



青岛思诺碳素有限公司

QINGDAO SINO CARBON CO., LTD.

地址: 中国·山东·青岛
电话: 0086-186 6986 0053
传真: 0086-532-83729505
邮箱: info@sinoelectrode.com
网址: www.sinoelectrode.com

Address: Qingdao, Shandong, China
Tel: 0086-186 6986 0053
Fax: 0086-532-83729505
E-mail: info@sinoelectrode.com
<http://www.sinoelectrode.com>



Suggested Current Capacity and Current Density:

Diameter mm	RP		HP		UHP	
	Current Load (A)	Current Density (A/cm ²)	Current Load (A)	Current Density (A/cm ²)	Current Load (A)	Current Density (A/cm ²)
200	5000-6900	15-21	5500-9000	18-25		
250	7000-10000	14-20	8000-13000	18-25		
300	10000-13000	14-18	13000-17400	17-24	15000-22000	20-30
350	13500-18000	14-18	17400-24000	17-24	20000-30000	20-30
400	18000-23500	14-18	21000-32000	16-24	25000-40000	19-27
450	22000-27000	13-17	25000-40000	15-24	32000-45000	19-27
500	25000-32000	13-16	30000-48000	15-24	38000-55000	18-27
550	32000-41000	13-16	37000-58000	15-23	45000-65000	18-27
600	38000-47000	13-16	44000-67000	15-23	52000-75000	18-26
650	45000-54000	13-16	54000-73000	15-23	62000-95000	18-24

E-mail: info@sinoelectrode.com

<http://www.sinoelectrode.com>